

Chem-Impex International, Inc.

Tel: (630) 766-2112

E-mail: sales@chemimpex.com

Shipping and Correspondence:

935 Dillon Drive

Wood Dale, IL 60191

Fax: (630) 766-2218

Web site: www.chemimpex.com

Manufacturing site:

825 Dillon Drive

Wood Dale, IL 60191

Certificate of Analysis

Catalogue Number	03538
Lot Number	000954-0601-1
Product	Rink amide AM resin (with Nle) 4-(2',4'-Dimethoxyphenyl-Fmoc-aminomethyl) phenoxyacetamidonorleucylaminomethyl resin

Appearance	Pale white or slight yellow beads
Swelling in DCM	8.3 mL/g (1 g resin swelling in DCM for 4 h)
Swelling in DMF	7 mL/g (1 g resin swelling in DMF for 4 h)
Kaiser Test	Negative
Infrared Spectrum	Conforms to structure
Loss on Drying	0.45% (5 h in vacuum oven at 40±1 °C)
Mesh Size	200 - 400 mesh
Substitution (meq/g)	0.42 mmol/g
% DVB	1% DVB
Storage	Store at RT
Remarks	See material safety data sheet for additional information For laboratory use only

The foregoing is a copy of the Certificate of Analysis as provided by our supplier



Bala Kumar
Quality Control Manager