

Chem-Impex International, Inc.

Tel: (630) 766-2112

E-mail: sales@chemimpex.com

Shipping and Correspondence:

935 Dillon Drive

Wood Dale, IL 60191


Fax: (630) 766-2218

Web site: www.chemimpex.com

Manufacturing site:

825 Dillon Drive

Wood Dale, IL 60191



Product Specifications

Catalogue Number	03541
Product	9-Fmoc-aminoxanthene-3-yloxy polystyrene resin (0.6-0.8 meq/g, 100-200 mesh) Sieber resin Sieber amide resin
CAS Number	915706-90-0
Appearance	Pale white or slight yellow beads
Swelling in DCM	5 - 8 mL/g
Swelling in DMF	4 - 7 mL/g
Kaiser Test	Negative
Infrared Spectrum	Conforms to structure
Loss on Drying	≤ 2%
Mesh Size	100 - 200 mesh
Substitution (meq/g)	0.6 - 0.8 meq/g
% DVB	1% DVB
Storage	Store at 0 - 8 °C

For Laboratory Use Only