

Chem-Impex International, Inc.

Tel: (630) 766-2112

E-mail: sales@chemimpex.com

Shipping and Correspondence:

935 Dillon Drive

Wood Dale, IL 60191

Fax: (630) 766-2218

Web site: www.chemimpex.com

Manufacturing site:

825 Dillon Drive

Wood Dale, IL 60191

Product Specifications

Catalogue Number	33301
Product	9-Fmoc-aminoxanthen-3-yloxy-polystyrene resin Sieber resin

Appearance	Pale white or slight yellow beads
Kaiser Test	Negative
Infrared Spectrum	Conforms to structure
Loss on Drying	≤ 2% (5 h in vacuum oven at 40 ± 1 °C and 1 mmHg pressure)
Mesh Size	200 - 400 mesh
Substitution (meq/g)	0.2 - 0.6 mmol/g
% DVB	1% DVB
Storage	Store at 2 - 8 °C

For Laboratory Use Only